

## PRODUCT DATA SHEET

# webergROUT coarse

Abrasion resistance, cement based tile grout for wall and floor grouting with joint width of 5 – 12 mm complied with CG2WA class of EN 13888

### PRODUCT

**webergROUT coarse** is a cementitious single component tile grout. It is designed for grouting porous and vitreous tiles on interior or exterior walls and floors with joint width **5 – 12 mm**. The grout is shrinkage compensated which can prevent cracking. **webergROUT coarse** has low water absorption and high adhesion to tiles and tile adhesive. There is a wide range of colours available to match different tiles.

### Uses

- Grouting for ceramic, vitrified tile and marble that with joint width 5 – 12 mm
- Grouting for industrial flooring where resistance to chemical is not required

### Features and Benefits

- Formulated to comply with European Norm, American Standard, British Standard and Chinese Standard
- Shrinkage compensated: reduce the chance of shrinkage cracks
- Good abrasion resistance
- Good compressive and flexural strength
- Resistance to acidic cleanser with pH > 3

### TECHNICAL DATA

Colour	Custom
Component	Portland cement, non-reactive aggregate, graded sand and other chemical additives
Max. aggregate size	1 mm
Water demand	Grey and other colours : Approx. 15 - 18% (3.8 – 4.5 L/25 KG bag) White : Approx. 18 – 21% (4.5 – 5.3 L/25 KG bag)
Density	1.4 g/cm <sup>3</sup>
Pot life	Approx. 1 hour
Coverage	Approx. 1.7 kg/m <sup>2</sup> /mm



Saint-Gobain Weber (Hong Kong) Building Material Co., Limited  
聖戈班偉伯(香港)建材有限公司

Page 1 | 3

## THEORETICAL CONSUMPTION ON THE SIZE OF TILE

Tile dimension (mm)			Total Consumption (kg/m <sup>2</sup> )			
			Joint width (mm)			
Length	Width	Thickness	5 (mm)	8 (mm)	10 (mm)	12 (mm)
300	300	8	<b>0.5</b>	<b>0.7</b>	<b>0.9</b>	
300	300	10	<b>0.6</b>	<b>0.9</b>	<b>1.1</b>	
300	300	20	<b>1.1</b>	<b>1.8</b>	<b>2.3</b>	<b>2.7</b>
300	600	10	<b>0.4</b>	<b>0.7</b>	<b>0.9</b>	
330	330	10	<b>0.5</b>	<b>0.8</b>	<b>1.0</b>	
450	450	12	<b>0.5</b>	<b>0.7</b>	<b>0.9</b>	<b>1.1</b>
600	600	12	<b>0.3</b>	<b>0.5</b>	<b>0.7</b>	<b>0.8</b>

$$\text{Total consumption (kg/m}^2\text{)} = \frac{(\text{Tile length} + \text{Tile width}) \times \text{Tile thickness} \times \text{Gap width}}{\text{Tile length} \times \text{Tile width}} \times \text{Coverage (kg/m}^2\text{/mm)}$$

## PHYSICAL PROPERTIES

Abrasion resistance	EN 12808-2	< 1,000 mm <sup>3</sup>
Compressive strength	EN 12808-3 • After dry storage • After freeze-thaw cycle	≥ 15 N/mm <sup>2</sup> ≥ 15 N/mm <sup>2</sup>
Flexural strength	EN 12808-3 • After dry storage • After freeze-thaw cycle	≥ 3.5 N/mm <sup>2</sup> ≥ 3.5 N/mm <sup>2</sup>
Linear shrinkage	ANSI A 118.6-1992 • After 24 hours • After 7 days EN 12808-4 • After 28 days	≤ 0.5 mm/m ≤ 1.5 mm/m ≤ 2 mm/m
Water absorption	EN 12808-5 • After 30 minutes • After 240 minutes	≤ 2 g ≤ 5 g
Water absorption	ANSI A 118.6-1992 • 50% R.H. to immersion • Immersion to dry	< 5 % < 7 %
Resistance to mould growth	BS 5980 : 1980	No mould growth
Tensile strength	BS 5980 : 1980	1000 N

Unless specified, all technical data refers to 28 days curing time.

Above physical data are taken on laboratory tests. In situ material performance may vary according to environmental & workmanship conditions beyond manufacturer control.

### **Complied Standards**

European Norm	:	EN 13888 : 2002 Class CG2WA
American Standard	:	ANSI A118.6 : 1992, USEPA method 24
British Standard	:	BS 5980 : 1980 Part 7. 9
Chinese Standard	:	JC/T 1004 : 2006 Class CG2WA

## **PROCEDURE**

### **Substrate Preparations**

Substrate must be free from grease, mould oil, rust, rusty metal, wood peels, paints, plastics, loose particles, contamination on any traces of foreign materials affecting the adhesion of **webergROUT coarse**.

### **Mixing and Installation**

**webergROUT coarse** can be applied at least 1 day after tiling.

Before application, dampen the surface with clean water and allow excess water to drain away.

Mix a bag of dry-mixed powder (25 KG) with appropriate amount of water by using an electrical mixer. Add approx. 15 – 18% (3.8 – 4.5 L) of water for grey powder / 18 – 21% (4.5 – 5.3 L) of water for white powder.

Stir the mixture thoroughly for 5 – 7 minutes to obtain a creamy paste without lumps.

Apply **webergROUT coarse** grouting mortar to the tiled wall with a rubber, or sponge trowel, or other suitable tool diagonally over the tiles. Force and compact maximum amount of grout deep into the joints.

Excess grout on the tiles should be wiped away diagonally by using a rubber or sponge trowel.

Allow the grout to dry for 15 – 30 minutes, depending on temperature and humidity, then clean the tile surface by a damp coarse cloth or sponge. The cloth or sponge shall be dry enough to minimize “pulling” or “shirking” of joint.

If grout haze or film is found on the surface of the tile after grouting, it shall be removed as quickly as possible, preferably within 1 hour.

Please refer to our method statement for procedures in details.

### **Curing**

Natural air curing is enough for **webergROUT coarse**.

## **STORAGE AND PACKING**

**webergROUT coarse** is delivered in 25 kg bag. Storage life is 12 months if the product is kept in a dry place.

## **HEALTH AND SAFETY**

Recommend to wear NIOSH approved or equivalent particulate face mask when mixing the material. Material contains cement, which may produce an allergic effect.

Keep out of reach of children.

Material may cause irritation to eyes and skin. In case of contact with eyes, rinse immediately with plenty of water and seek medical assistance. After contact with skin, wash immediately with plenty of soap and water.

Please refer to Material Safety Data Sheet (MSDS) for health, safety and handling of the product.

\* Note: The information and physical data in this catalogue is given to the best of our knowledge under standard testing method and controlled environment. The results may vary with different weather / site conditions, workmanship or substrates. This is beyond our control that we shall not be liable for any faults or consequences arising or associated with this. We suggest comprehensive tests to be conducted before final application. Unless specified, all technical data are average values with curing time of 28 days. We reserve the right to update or amend the contents in the light of new findings during the course of research and development.